

# “525.Tyrefield”

## DESCRIPTION

Sistema di pavimentazione modulare permeabile per rivestimento ad uso sportivo, realizzata con gomma riciclata da Pneumatici Fuori Uso (PFU), 100% riciclabile.

## DIMENSIONAL DATA

Misura piastrella	EN 427	33,25x33,25 cm
Spessore piastrella	EN 428	1,8 cm
Peso	EN 430	760.gr/piastrella (6,8kg/mq ca.)

## SPORTS DATA

Shock Absorption	EN 14808	12
Sh. Ab. with shockpad	EN 14808	30 (28 after aging)
Vertical deformation	EN 14809	0,4
V. def with shockpad	EN 14809	1,6
Slip resistance	EN 13036-4	Dry/Wet 95/56
Vertical Ball rebound	EN 12235	99
V.B.Re. with shockpad	EN 12235	102
Water permeability	EN 12616	35065 / 36999

## TENSILE PROPERTIES AND RESISTANCES

Tensile Strength (and a.a.a.)	EN 12230	3,18 – 3,68
Resistance to wear	EN ISO 5470-1	0,07
Resistance to artificial Weathering	EN ISO 20105-A02	4-5
Taber test after UV	(colour Fastness):	<4    0,16

## FIBA “REQUIREMENTS”

Shock Absorption	EN 14808	>11 Level 2   >25 Level 1
Vertical deformation	EN 14809	<3,5
Slip resistance	EN 13036-4	Dry 80-110   Wet 55-110
Vertical Ball rebound	EN 12235	>90 Level 1

Laboratory test report nr. 61547 e 61682 by Sports Labs

